

Edited by:

Farhat Yasmeen

Peer Review policy:

Double-blind

***Correspondence:**

karimchem@gmail.com

¹Bacha khan university

²University of Swat

³Abdul Wali khan University

Citation:

Karim et al. (2024) Synthesis and Characterization of Selenium-Reduced Graphene Oxide with Cobalt Acetate Nanoparticles. 1(1):06-09.

Uoi: 06-09-01(1)2024IR24-08

Peer-reviewed

Open access

**E-magazine by Innovative
Scientific Information &
Services Network**

Available online at

www.isisn.org



Synthesis and Characterization of Selenium-Reduced Graphene Oxide with Cobalt Acetate Nanoparticles"

Muhammad Karim¹, Sardar Hussain², Jawad Ikram², Safeer Ahmad Khan², Rahat Ullah¹ and Muhammad Ibrahim³

Published: 21 November 2024

The Oxygen Reduction Reaction (ORR) is a key process in the electrochemical performance of Proton Exchange Membrane Fuel Cells (PEMFCs). Precious metal electro catalysts are traditionally used at the cathode due to their efficiency in catalyzing ORR at low temperatures. However, the development of alternative catalysts using non-precious materials is essential for cost reduction and sustainability. In this study, we successfully synthesized selenium-reduced graphene oxide (Se-rGO) combined with cobalt acetate nanoparticles as a potential ORR catalyst. The synthesized materials were characterized using X-ray diffraction (XRD) to verify the presence of selenium, graphene, and cobalt, confirmed through specific diffraction peaks. Fourier Transform Infrared Spectroscopy (FTIR) was employed to identify functional groups, while the morphology and structure were examined via Scanning Electron Microscopy (SEM). Additionally, elemental composition analysis using Energy Dispersive X-ray Spectroscopy (EDAX) confirmed the incorporation of selenium, graphene, and cobalt in the synthesized catalyst.

Keywords: Oxygen Reduction Reaction, grapheme, cobalt, catalysts, fuel cells

INTRODUCTION

The problems of global warming, environmental pollution and energy risk were drawn greater attentions for the development of clean and sustainable energy sources (Gu, Hu, Li, & Wang, 2018). The newly emerging field of nanotechnology has the potential to make a significant impact on the electro catalysts for the ORR by introducing novel nano scale materials (Zhu Chen, Higgins, Tao, Hsu, & Chen, 2009). The fuel cells have been receiving a lot of attention as a sustainable power source for transport, sustainable and portable applications because of their efficiency and low emission (Campos-Roldán et al. 2016). The Proton Exchange Membrane Fuel Cell (PEMFC) is considerable as an ideal power source for mobile and stationary applications (Sa et al. 2014). The oxygen reduction reaction plays an important role in the overall performance of electrochemical energy devices, such as fuel cells and metal air batteries (Zhou et al. 2013). The exploration of non- precious metal catalysts with high efficiency, low cost and superior durability to oxygen reduction reaction have been conducted as promising candidates to replace platinum based catalysts such as transition metals, nitrogen, carbon and etc. (Sun et al. 2018). The transition metals shows catalytic behavior mainly due to the presence of vacant 'd' orbital and the ability to exhibit variable vacancies and the tendency to form complex compounds (Song et al. 2018). TMOs have received considerable attention as anodic materials for use in batteries because of their superior theoretical capacity. Graphene, improves the conductivity, because it has a high surface area, good mechanical properties and high electrical conductivity, which help in improving the electrochemical properties of metal oxides (Zhongwei Chen, Dodelet, & Zhang, 2014). Recently a large number of reports has been published on ORR electro catalysts, to reduce the cost of fuel cells electro catalysts, Two major approaches are currently very active i) To increase the platinum catalytic activity and reduce Pt content through alloying with other transition metal oxides such as Cr, Ni, Fe, Co and so on, ii) To improve the Pt utilization by increasing the surface area and dispersion of Pt nano particles using high surface carbon supports (Unni, Mora-Hernandez, Kurungot, & Alonso-Vante, 2015). TMOs have received attention ex. HER (Tian, Zhou, Sun, Ding, & Wang, 2007),

ORR (Zhang, 2008), and solar cells due to their multifunction behavior and thus important as catalysts in PEMFC and ease of synthesis (Chao, Tsai, Wu, Tseng, & Huang, 2013). From these approaches we are prepared the materials by using the transition metal oxides. In the D block elements, The cobalt has greater ability in accepting atoms from other molecules and forming complex molecules needed in further chemical reactions, process and the cobalt can react to form more than one ion to exhibit catalysis thus allowing for a wider variety of reactions (Baerlocher & McCusker, 1994). So we focus alloying the precious metal with another metal in order to increase the mass activity with respect to platinum and eliminating the need for platinum by producing non precious metal catalysts that can match platinum in catalytic activity.

Materials and Method

Preparation of Se-rGO and CoSe₂/Se - rGO

200 mg of graphite oxide was ultrasonically dispersed into 100 ml deionized water at 45°C, then under stirring the 200mg of SeO₂ was added into the suspension of GO. The temperature maintained at 80° C for 2 hrs. Then the reducing agent hydrazine hydrate was dropped into the mixture. The resulting mixture was filtered by using whatmann filter paper and the prepared sample was washed well with deionized water and freeze drying. The product was labeled as Se-rGO. Similarly for the preparation CoSe₂/Se-rGO, 0.023g of Na₂ SeO₃ is dissolved in 13 ml of Diethylene Triamine (DETA) solution to prepare solution A and 0.1350 g of Se-rGO and 0.0172 g of Co(AC)₂. H₂O is dispersed in 26 ml of water to prepare solution B. the two solutions were transferred to an autoclave, which was maintained at 180°C for 16 hrs. Then the system was left cooled down to room temperature. The product was filtered by using whatmann filter paper and washed well with deionized water and freeze drying. The product was labeled as CoSe₂/Se-rGO.

Results and Discussions

X-Ray Diffraction & FTIR Spectrum Analysis

The presence of phase structural transformation of the synthesized Se-r Go and Co Se₂/Se-rGo sample was characterized by X-Ray diffraction. X-Ray diffraction detection on a PAN analytical Xpert 3 with a Cu K α radiation ($\lambda=1.541\text{\AA}$). High intense peaks are noticed in the X-Ray diffraction pattern of the Se-r Go and Co Se₂/Se-rGo material, which confirm the nano crystalline nature of the material, the pattern does not contain any impurity peak, which confirm the purity of the material and phase. The broad diffraction beak Between 20° to 30° shows the presence of carbon. The crystalline size was calculated using the Debye Scherer's formula. From the XRD results calculate the crystallite size of the materials was calculated using the relation. The calculated crystalline size was 34nm. The peak position at $2\theta = 26.30, 29.44, 44.23$ confirm the presence of Selenium and cobalt. The FTIR spectra for all prepared samples are analysed using Bruker, Alpha T, model spectrometer and it ions recorded by KBr pellet technique from the range of 4000cm⁻¹ to 4000 cm⁻¹. Fourier Transform spectroscopy is a technique which is used to obtain an infrared spectrum and to measure the vibrational frequencies of bonds in the molecule. Fig 3 shows the FTIR spectra of prepared Se-rGo nano material, well defined absorption bands were observed at 586.61 cm⁻¹ and 671 cm⁻¹ which is assigned at Co-O stretching vibration and O-Co-O bridging vibration. The wave length at 1107 cm⁻¹ and 1402 cm⁻¹ assigned at alkoxy group and carboxyl C-O. The wave length at 1626 cm⁻¹ assigned at unoxidized graphitic domains. Fig 4 shows that the FTIR spectra of Co Se₂/Se- rGo. The wavelength at 1052 cm⁻¹ and 1251 cm⁻¹ confirm the stretching vibration of C-O according to standard spectrum of cobalt acetate peak should be at frequency range 2980 cm⁻¹ and 3526 cm⁻¹ assigned the O-H bands [24]. 1649 cm⁻¹ and the C-H bands near 2980 cm⁻¹ are due to the presence of cobalt acetate residue.




Figure 1,2 :XRD spectra and figure 3, 4 shows FTIR spectra of Se-rGO and CoSe₂/Se – rGO respectively

Sem and edax analysis

Scanning electron microscopy is used for inspecting topographic of specimens at very high magnifications using a piece of equipment called the Scanning Electron Microscope. In order to obtain insight information about surface morphology and particle size of the samples, SEM analyses were performed. SEM analysis was carried out using Carl Zeiss EVO 18 at 25 Kx magnifications. The morphology of the synthesized Se-rGO and CoSe₂/Se-rGO nano materials examined by the SEM was shown in Fig 5&6. The Energy spectrum analysis technique was used to determine the composition of the sample. The EDAX spectrum of Se-rGO Fig (7) shows the presence of selenium, at 2KeV the presence of grapheme were present in the prepared sample. No appreciable quantities of Cu were observed over a number of surface sites. The EDAX spectrum of Co Se₂/Se-rGo Fig (8) shows the presence of cobalt and selenium, so it will be confirmed that cobalt is assisted with selenium.




Figure 5, 6: shows SEM images of Se-rGO and CoSe₂/Se – rGO and 7,8 shows EDAX spectra of Se-rGO and CoSe₂/Se – rGO respectively

CONCLUSION

Selenium decorated reduced grapheme oxide (Se-rGo) was successfully prepared and CoSe₂ was assisted into the Se-rGo, the phase structure and crystalline size were determined by the X Ray Diffraction analysis. The functional groups were presented in the prepared sample were identified using FTIR analysis. The morphology and composition of the prepared samples were analysed by Scanning Electron Microscope and EDAX.

CONFLICT OF INTEREST

The authors declare no conflict of interest.

ACKNOWLEDGEMENT

Thanks to all authors for their team work

Copyrights: © 2024@ author (s).

This is an open access article distributed under the terms of the [Creative Commons Attribution License \(CC BY 4.0\)](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original author(s) and source are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.

REFERENCES

- Baerlocher, C., & McCusker, L. B. (1994). Practical aspects of powder diffraction data analysis. In *Studies in Surface Science and Catalysis* (Vol. 85, pp. 391-428): Elsevier.
- Campos-Roldán, C. A., Ramos-Sánchez, G., Gonzalez-Huerta, R. G., Vargas Garcia, J. R., Balbuena, P. B., & Alonso-Vante, N. (2016). Influence of sp³–sp² carbon nanodomains on metal/support interaction, catalyst durability, and catalytic activity for the oxygen reduction reaction. *ACS applied materials & interfaces*, 8(35), 23260-23269.
- Chao, Y.-S., Tsai, D.-S., Wu, A.-P., Tseng, L.-W., & Huang, Y.-S. (2013). Cobalt selenide electrocatalyst supported by nitrogen-doped carbon and its stable activity toward oxygen reduction reaction. *International journal of hydrogen energy*, 38(14), 5655-5664.
- Chen, Z., Dodelet, J.-P., & Zhang, J. (2014). *Non-noble metal fuel cell catalysts*: John Wiley & Sons.
- Chen, Z., Higgins, D., Tao, H., Hsu, R. S., & Chen, Z. (2009). Highly active nitrogen-doped carbon nanotubes for oxygen reduction reaction in fuel cell applications. *The Journal of Physical Chemistry C*, 113(49), 21008-21013.
- Gu, W., Hu, L., Li, J., & Wang, E. (2018). Recent advancements in transition metal-nitrogen-carbon catalysts for oxygen reduction reaction. *Electroanalysis*, 30(7), 1217-1228.
- Sa, Y. J., Park, C., Jeong, H. Y., Park, S. H., Lee, Z., Kim, K. T., . . . Joo, S. H. (2014). Carbon nanotubes/heteroatom-doped carbon core–sheath nanostructures as highly active, metal-free oxygen reduction electrocatalysts for alkaline fuel cells. *Angewandte Chemie*, 126(16), 4186-4190.
- Song, F., Bai, L., Moysiadou, A., Lee, S., Hu, C., Liardet, L., & Hu, X. (2018). Transition metal oxides as electrocatalysts for the oxygen evolution reaction in alkaline solutions: an application-inspired renaissance. *Journal of the American Chemical Society*, 140(25), 7748-7759.
- Sun, X., Olivos-Suarez, A. I., Osadchii, D., Romero, M. J. V., Kapteijn, F., & Gascon, J. (2018). Single cobalt sites in mesoporous N-doped carbon matrix for selective catalytic hydrogenation of nitroarenes. *Journal of catalysis*, 357, 20-28.
- Tian, N., Zhou, Z.-Y., Sun, S.-G., Ding, Y., & Wang, Z. L. (2007). Synthesis of tetrahedral platinum nanocrystals with high-index facets and high electro-oxidation activity. *science*, 316(5825), 732-735.
- Unni, S. M., Mora-Hernandez, J. M., Kurungot, S., & Alonso-Vante, N. (2015). CoSe₂ Supported on Nitrogen-Doped Carbon Nanohorns as a Methanol-Tolerant Cathode for Air-Breathing Microfluidic Flow Fuel Cells. *ChemElectroChem*, 2(9), 1339-1345.
- Zhang, J. (2008). *PEM fuel cell electrocatalysts and catalyst layers: fundamentals and applications*: Springer Science & Business Media.
- Zhou, W., Wu, X.-J., Cao, X., Huang, X., Tan, C., Tian, J., . . . Zhang, H. (2013). Ni₃S₂ nanorods/Ni foam composite electrode with low overpotential for electrocatalytic oxygen evolution. *Energy & Environmental Science*, 6(10), 2921-2924.